

Santa Clara



Location:

Santa Clara, CA

Trim:

98"

Caliper Range:

.007" - .015"

Rolls:

- ✓ Widths 3" to 98"
- √ 55" 72" diameters
- ✓ 4" cores
- ✓ Ribbon slit tolerance: ± 1/16"

Certifications:

- ✓ FSC®, SFI® and PEFC® Chain of Custody Standard for Recycled Paper
- ✓ FDA® Compliant for Dry Food Packaging
 - 21 CFR 176.170
 - 21 CFR 176.18
 - 21 CFR 176.260
- ✔ RPTA 100% Certified

Product Offerings:

- Recycled Corrugating Medium 23# to 45# Basis Wt.
- ✓ Recycled WS Medium 23# to 45# Basis Wt.
- ✓ Recycled HP Medium 23# Basis Wt.
- Recycled HS WS Medium 23# Basis Wt.
- Recycled Linerboard
 - With or without wet strength
 - 35# to 56# Basis Wt.



Containerboard (CB) Mills

Santa Clara page 2

	Basis Weights/Grades								
Recyled Medium Specifications	23M	26M	30M	33M	36M	38M	40M	45M	
Basis Weight (Lbs/MSF) Tappi T410									
Nominal	23	26	30	33	36	38	40	45	
Moisture, Average (%)									
Max	9	9.5	9.5	9.5	9.5	9.5	9.5	9.5	
Average	8.25	8.5	8.5	8.5	8.5	8.5	8.5	8.5	
Min	7.75	8	8	8	8	8	8	8	
Moisture Variation (%)									
CD 2-Sigma, Max	3	3	3	3	3	3	3	3	
Caliper (Mils) Tappi T411									
Range, ±	.001	.001	.001	.001	.001	.001	.001	.001	
Concora Medium Test (Lbs-f) Tappi T809									
Target	55	60	62	65	70	73	75	77	
Cross Direction Ring Crush (Lbs) Tappi T822									
Target		30	38	44	45	50	65	69	
Float Curl (Sec) Tappi T832									

Porosity (Sec/100cc) Tappi T460

Recyled Linerboard Specifications	33L	35L	35HPL	42L	56L	69L
Basis Weight (Lbs/MSF) Tappi T410						
Nominal	33	35	35	42	56	69
Moisture, Average (%) Tappi T412						
Average	7	7	7	7	7	7
Range, ±	.75	.75	.75	.75	.75	.75
Moisture Variation/C.D. 2-Sigma (Max)	3	3	3	3	3	3
Caliper (Mils) Tappi T411						
Range ±	.001	.001	.001	.001	.001	.001
Mullen (PSI) Tappi T807						
Cross Direction Ring Crush (Lbs)						
Tappi T822						
Target	75	70	75	84	112	138
Cobb (2-Min) (GSM) Tappi T441						
Target	45	45	45	45	45	45
Porosity (Sec/100cc) Tappi T460						

Tappi Dirt Count Tappi T537

• For more information: 1-408-567-9807

